

**Listing of Claims**

The following listing of claims replaces all prior versions and listings of claims in the application.

1. (Original): An optical film comprising:  
a transparent polymer film (b); and  
a birefringent layer (a) formed of a polymer and laminated above the transparent polymer film (b),

wherein the birefringent layer (a) and the transparent polymer film (b) satisfy a formula (1) below,

the birefringent layer (a) satisfies formulae (2) and (3) below, and

the polymer forming the birefringent layer (a) has a weight-average molecular weight in a range between 10,000 and 400,000 inclusive,

$$\Delta n(a) > \Delta n(b) \times 10 \quad (1)$$

$$1 < (n_x - n_z) / (n_x - n_y) \quad (2)$$

$$0.0005 \leq \Delta n(a) \leq 0.5 \quad (3)$$

where  $\Delta n(a)$  is a birefringence of the birefringent layer (a) and is represented by  $[(n_x + n_y) / 2] - n_z$ ,

$\Delta n(b)$  is a birefringence of the transparent polymer film (b) and is represented by  $[(n_x' + n_y') / 2] - n_z'$ ,

$n_x$ ,  $n_y$ , and  $n_z$  represent refractive indices in an X-axis direction, a Y-axis direction, and a Z-axis direction in the birefringent layer (a), respectively, with the X-axis direction being an axial direction exhibiting a maximum refractive index within a plane of the birefringent layer (a), the Y-axis direction being an axial direction perpendicular to the X-axis within the plane, and the Z-axis direction being a thickness direction perpendicular to the X-axis and the Y-axis, and

$n_x'$ ,  $n_y'$ , and  $n_z'$  represent refractive indices in an X-axis direction, a Y-axis direction, and a Z-axis direction in the transparent polymer film (b), respectively, with the X-axis direction

being an axial direction exhibiting a maximum refractive index within a plane of the transparent polymer film (b), the Y-axis direction being an axial direction perpendicular to the X-axis within the plane, the Z-axis direction being a thickness direction perpendicular to the X-axis and the Y-axis.

2. (Original): The optical film according to claim 1, wherein the birefringent layer (a) is laminated directly on the transparent polymer film (b).

3. (Original): The optical film according to claim 1, wherein the polymer forming the birefringent layer (a) is a non-liquid crystalline polymer.

4. (Original): The optical film according to claim 3, wherein the non-liquid crystalline polymer is at least one polymer selected from the group consisting of polyamide, polyimide, polyester, polyetherketone, polyaryletherketone, polyamide imide, and polyesterimide.

5. (Original): The optical film according to claim 1, wherein the transparent polymer film (b) is a protective film for a polarizer.

6. (Original): The optical film according to claim 1, wherein the transparent polymer film (b) is a polarizer comprising a polyvinyl alcohol-based film.

7. (Original): A laminated polarizing plate comprising an optical film, wherein the optical film is the optical film according to claim 1.

8. (Currently amended): A liquid crystal panel comprising a liquid crystal cell and an optical member, the optical member being arranged on at least one surface of the liquid crystal cell, wherein the optical member is the optical film according to claim 1 ~~or the laminated polarizing plate according to claim 7.~~

9. (Original): A liquid crystal display comprising a liquid crystal panel, wherein the liquid crystal panel is the liquid crystal panel according to claim 8.

10. (Currently amended): A self-light-emitting display comprising the optical film according to claim 1 ~~or the laminated polarizing plate according to claim 7.~~

11. (New): A liquid crystal panel comprising a liquid crystal cell and an optical member, the optical member being arranged on at least one surface of the liquid crystal cell, wherein the optical member is the laminated polarizing plate according to claim 7.

12. (New): A liquid crystal display comprising a liquid crystal panel, wherein the liquid crystal panel is the liquid crystal panel according to claim 11.

13. (New): A self-light-emitting display comprising the laminated polarizing plate according to claim 7.

14. (New): A display comprising the optical film according to claim 1.

15. (New): A display comprising the laminated polarizing plate according to claim 7.

16. (New): The laminated polarizing plate according to claim 7, wherein the transparent polymer film (b) is a protective film for a polarizer.

17. (New): An optical element comprising the optical film of claim 1 and a birefringent film.